

Technical data sheet in accordance with ASTM

Material

FKM FP803403

brown

cross linking: bisphenolically

revision index	revision date	page	1 / 3
3	4/11/2017		

Physical properties	nominal range	typical values	
Density ASTM D 1817	2.16 ±0.03	2.16	g/cm ³
Hardness ASTM D2240, Shore A	80 ±5	80	Shore
Tensile strength ASTM D412	---	13.8	MPa
Elongation at Break ASTM D412	---	202	%
Low-temperature resistance ASTM D 2137, 3 min, pass	---	-25	
Compression set ASTM D395, B, 22 h, 200 °C, 25 %	---	12	%
Temperature range	-25°C to 200°C		

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
ADI Free			see certificate		<input checked="" type="checkbox"/>
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>

Change after aging in Air: 70h/250°C

		Typ. values		
		Base value	After aging	difference
Hardness (ASTM D2240, Shore A)	Shore	80	84	4
Tensile strength (ASTM D412)	MPa	13.8	16.3	18 %
Elongation at Break (ASTM D412)	%	202	153.5	-24 %
volume change (ASTM D471)	%		-3	

Freudenberg

 Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner

 Telefon: +49 6201 80 2182
 Fax: -
 Email: nadja.gueldner@fst.com


Technical data sheet in accordance with ASTM

Material

FKM FP803403

brown

cross linking: bisphenolically

revision index

3

revision date

4/11/2017

page 2 / 3

Change after aging in ASTM service fluid # 101: 70h/200°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at Break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
80	71	-9	
13.8	10.8	-22 %	
202	220	9 %	
	12		

Change after aging in Fuel C: 70h/23°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at Break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
80	77	-3	
13.8	11.5	-17 %	
202	173.7	-14 %	
	4		

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: +49 6201 80 2182
Fax: -
Email: nadja.gueldner@fst.com



Technical data sheet in accordance with ASTM

Material

FKM FP803403

brown

cross linking: bisphenolically

revision index

3

revision date

4/11/2017

page

3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner

Telefon: +49 6201 80 2182
Fax: -
Email: nadja.gueldner@fst.com

